



AMIS0250

Certified Reference Material

**Fluorite, Witkop Flourspar Mine
Zeerust, South Africa**

Certificate of Analysis

Recommended Concentrations and Limits^{1,2} (at two Standard Deviations)

Certified Concentrations

F ISE ³	8.99	±	0.46	%
U M/ICP	6.5	±	0.8	ppm
Specific Gravity	2.93	±	0.08	

Provisional Concentrations

Th M/ICP	1.20	±	0.22	ppm
----------	------	---	------	-----

1. *Manufacturers recommended limits for use of the material as control samples, based on two standard deviations, calculated using "Between Laboratory" statistics for treatment of the data for trivial, non-trivial and technically invalid results. See sections 1, 9 and 12.*
2. *There is additional certified major element data presented on p2 and uncertified trace element data presented as an appendix.*
3. *Or, by applying a chemical conversion factor $F \times 2.0547 = CaF_2$; $CaF_2 = 18.472\%$*

Major Element Recommended Concentrations and Limits (at two Standard Deviations)

Certified Concentrations

CaO	36.32	±	0.42	%
Fe ₂ O ₃	2.93	±	0.06	%
MgO	14.77	±	0.90	%
MnO	0.84	±	0.06	%
SiO ₂	3.93	±	0.20	%
LOI	33.50	±	0.60	%

Provisional Concentrations

Al ₂ O ₃	0.44	±	0.10	%
--------------------------------	------	---	------	---

Informational Means

K ₂ O	0.12	%
P ₂ O ₅	0.04	%
TiO ₂	0.02	%

- 1. Intended Use:** AMIS0250 can be used to check analysis of samples of fluorite bearing rocks with a similar grade and matrix.

It is a matrix matched Certified Reference Material, fit for use as control samples in routine assay laboratory quality control when inserted within runs of samples and measured in parallel to the unknown. Its purpose is to monitor inter-laboratory or instrument bias and within lab precision. It can be used, indirectly, to establish the traceability of results to an SI system of units.

The recommended concentrations and limits for this material are property values based on a measurement campaign (round robin) and reflect consensus results from the laboratories that participated in the round robin.

Slight variations in analytical procedures between laboratories will reflect as slight biases to the recommended concentrations (see 19). Good laboratories will report results within the two standard deviation levels with a failure rate of <10 %.

The CRM can also be used for method development and for the calibration of equipment.

- 2. Origin of Material:** AMIS0250 is a commissioned CRM made up of material supplied by ENRC from the Witkop Fluorspar Mine; 18km south of the town of Zeerust and 115 km west of Rustenburg, in the North West Province of South Africa. The Witkop fluorspar deposits are large bedded replacement deposits of the classical Mississippi Valley type. They occur in the Transvaal Basin, within 2550 million year old dolomites of the Malmani Subgroup, Transvaal Supergroup. Fluorspar mineralisation occurs mainly associated with stromatolites in the Middle Frisco Zone and appears to have been introduced post deposition by hydrothermal brines. The fluorite occurs as a filling in permeable beds; within small gas cavities in the stromatolites.

- 3. Mineral and Chemical Composition:** Mineralogically this ore is primarily dolomite with fluorite. Major other minerals are calcite, mica, and talc (3% to 10%); with traces of quartz,

sulphides and chlorite. The sulphides make up <3%, dominantly pyrite, with minor pyrrhotite, sphalerite and galena.

4. Appearance: The material is a very fine powder. It is colored a Medium Light Grey (Corstor 10Y 6/2).

5. Handling instructions: The material is packaged in Laboratory Packs and Explorer Packs that must be shaken or otherwise agitated before use. Normal safety precautions for handling fine particulate matter are suggested, such as the use of safety glasses, breathing protection, gloves and a laboratory coat.

6. Method of Preparation: The ore is crushed, then dry-milled and air classified to 100% <54 μ . This fine powder is mixed in a blender for 14 hours and then split down into numbered 1 kg tubs. These lots are sampled for quality control and for round robin analysis. Quality control will typically comprise sampling 30 tubs selected from the whole stream. Round robin samples are selected the same way, so that one laboratory will receive samples from the beginning, end, and from throughout the batch.

7. Methods of Analysis requested:

1. Fluoride – Ion Selective Electrode.
2. Multi element scan to include U & Th. Multi-acid total digestion, ICP-OES or ICP-MS.
3. Majors (Al₂O₃, CaO, Cr₂O₃, Fe₂O₃, K₂O, MgO, MnO, Na₂O, SiO₂, TiO₂. LOI.) XRF fusion.
4. SG (gas pycnometer).

8. Information requested:

1. State and provide brief description of analytical techniques used.
2. State aliquots used for all determinations.
3. Results for individual analyses to be reported (not averages)
4. All results for Rare Earth Elements to be reported in ppm (not as oxides).
5. All results for multi-element scans to be reported in ppm.
6. All results for major elements to be reported in %, as oxides.
7. Report all QC data, to include replicates, blanks and certified reference materials used.

9. Method of Certification: Sixteen laboratories were each given eight randomly selected packages of sample. Fourteen of the laboratories submitted results.

Final limits were calculated after first determining if all data was compatible within a spread normally expected for similar analytical methods done by reputable laboratories. Data from any one laboratory was then removed from further calculations when the mean of all analyses from that laboratory failed a “t test” of the global means of the other laboratories. The means and standard deviations were then re-calculated using all remaining data. Any analysis that fell outside of the new two standard deviations was removed from the ensuing data base. The mean and standard deviations were again calculated using the remaining data.

The “between-laboratory” standard deviation is used in the calculation to eliminate technically and statistically invalid data. Upper and lower limits are based on the standard deviation of the remaining data, which reflect individual analyses and can be used to monitor accuracy in routine laboratory quality control. This is different to limits based on standard deviations derived from grouped set of analyses (see 12), which provide important measures for precision and trueness, but which are less useful for routine QC.

Standards with an RSD of near or less than 5 % are termed “Certified”, RSD’s of between near 5 % and 15 % are termed “Provisional”, and RSD’s over 15 % are termed “Informational”.

10. Participating Laboratories: The 14 out of 16 laboratories that provided results timeously were (not in same order as in the table of assays):

- 1 Activation Laboratories Pty Ltd (ActLabs) CA
- 2 ALS Chemex Laboratory Group Brisbane Australia
- 3 ALS Chemex Laboratory Group Johannesburg SA
- 4 ALS Chemex Laboratory Group Perth WA
- 5 Genalysis Laboratory Services W Australia
- 6 Set Point Laboratories (Isando) SA
- 7 SGS Australia Pty Ltd (Newburn) WA
- 8 SGS Geosol Laboratories Ltda (Brazil)
- 9 SGS Mineral Services Callao (Peru)
- 10 SGS Mineral Services Lakefield (Canada)
- 11 SGS South Africa (Pty) Ltd - Booyens JHB
- 12 SGS Toronto (Canada)
- 13 Ultra Trace (Pty) Ltd WA
- 14 Vergenoeg Mining Company (SA)

11. Assay Data: Data as received from the laboratories for the important certified elements listed on p1 are set out below.

Lab Code	F ISE %	U M/ICP ppm	Th M/ICP ppm	Al2O3 XRF %	CaO XRF %	Cr2O3 XRF %	Fe2O3 XRF %	K2O XRF %	MgO XRF %	MnO XRF %	Na2O XRF %	P2O5 XRF %	SiO2 XRF %	SO3 XRF %	TiO2 XRF %	LOI XRF %	SG pycnometer
A	8.66			0.23	36.14		3.31	0.12	15.38	0.98		0.05	3.74			33.42	2.94
A	8.91			0.27	36.12		3.39	0.12	15.40	0.96		0.05	3.79			33.34	2.99
A	8.76			0.33	36.18		3.38	0.12	15.88	0.98		0.05	3.89			33.36	2.93
A	9.00			0.22	36.02		3.32	0.12	15.37	0.98		0.05	3.68			33.35	2.96
A	8.81			0.28	35.95		3.33	0.12	15.36	0.98		0.05	3.79			33.25	2.94
A	9.00			0.27	36.00		3.28	0.12	15.18	0.98		0.06	3.76			33.24	2.97
A	8.86			0.28	36.13		3.34	0.12	15.43	0.99		0.05	3.76			33.13	2.93
A	8.81			0.28	35.80		3.31	0.12	15.44	0.99		0.05	3.72			33.12	2.94
B	9.93	6.35	1.40														
B	9.36	6.58	1.30														
B	9.35	6.65	1.30														
B	9.72	6.23	1.40														
B	9.40	6.60	1.40														
B	9.68	6.97	1.30														
B	9.42	6.91	1.30														
B	9.29	6.53	1.30														
C		5.70	1.10														2.94
C		6.30	1.20														2.93
C		6.00	1.20														2.94
C		5.90	1.10														2.93
C		6.20	1.20														2.92
C		6.10	1.20														2.92
C		6.70	1.20														2.68
C		5.80	1.10														2.93
D	9.03	5.05															
D	9.18	5.47															
D	9.10	4.80															
D	8.92	5.00															
D	9.12	5.09															
D	9.04	5.05															
D	9.00	4.88															
D	8.90	5.06															
E				0.67			4.59					0.04	4.12				
E				0.67			4.59					0.03	4.08				
E				0.68			4.58					0.03	4.10				
E				0.67			4.57					0.03	4.09				
E				0.71			4.66					0.03	4.35				
E				0.67			4.57					0.04	4.09				
E				0.66			4.57					0.03	4.16				
E				0.67			4.58					0.03	4.11				
F	7.81	6.81	1.24	0.41	36.50		2.93	0.11	14.60	0.79	0.06		3.98		0.02	33.10	
F	7.40	6.57	1.17	0.40	36.60		2.96	0.11	14.50	0.80	0.06		3.91		0.02	32.80	
F	8.14	6.59	1.19	0.41	36.60		2.93	0.11	14.60	0.79	0.06		3.97		0.02	33.00	
F	7.26	6.46	1.16	0.40	36.50		2.94	0.11	14.50	0.80	0.05		3.90		0.02	32.90	
F	7.75	6.90	1.22	0.40	36.50		2.94	0.11	14.50	0.80	0.05		3.88		0.02	33.00	
F	7.63	6.73	1.18	0.41	36.60		2.95	0.10	14.60	0.80	0.05		3.96		0.02	33.00	
F	7.75	6.51	1.13	0.41	36.50		2.95	0.11	14.60	0.80	0.04		3.98		0.02	32.70	
F	7.53	6.89	1.22	0.41	36.60		2.93	0.11	14.60	0.79	0.05		3.94		0.02	32.50	
G	8.85	6.90	1.30	0.36	36.50		2.95	0.10	14.45	0.84	0.02		3.96			33.34	
G	8.91	7.10	1.40	0.35	36.20		2.90	0.10	14.25	0.82	0.03		3.94			33.00	
G	8.53	7.80	1.60	0.35	36.00		2.89	0.10	14.15	0.82	0.03		3.89			33.34	
G	8.82	7.10	1.30	0.35	36.30		2.92	0.10	14.30	0.83	0.02		3.88			32.52	
G	9.19	7.00	1.40	0.37	36.70		2.98	0.10	14.40	0.84	0.02		4.03			33.10	
G	8.78	6.60	1.30	0.38	36.20		2.93	0.10	14.25	0.82	0.02		4.12			33.29	
G	9.01	6.80	1.30	0.41	36.70		3.02	0.10	14.45	0.84	0.01		4.42			32.63	
G	8.67	7.70	1.40	0.36	36.10		2.89	0.10	14.20	0.82	0.01		3.86			32.78	
H	8.21		1.40	0.42	36.40		2.95	0.10	15.00	0.84		0.02	3.91			33.80	
H	7.87		1.40	0.44	36.30	0.02	2.90	0.11	15.00	0.85		0.04	4.03		0.02	33.70	
H	8.06		1.30	0.43	36.60	0.01	2.93	0.10	14.90	0.85		0.05	3.94		0.01	33.70	
H	8.50		1.30	0.44	36.70	0.02	2.95	0.10	15.00	0.85		0.04	3.97		0.01	33.70	
H	7.65		1.30	0.44	36.90	0.01	2.97	0.11	15.00	0.86		0.04	3.99		0.02	33.70	
H	8.88		1.20	0.42	36.30		2.90	0.10	14.90	0.83		0.02	3.83		0.02	33.80	
H	8.50		1.20	0.44	36.40	0.01	2.94	0.10	14.90	0.85		0.03	3.92		0.01	33.80	
H	8.45		1.30	0.44	36.90		2.93	0.10	15.10	0.87		0.04	4.01		0.01	33.80	

Assay data (cont)

Lab Code	F ISE %	U M/ICP ppm	Th M/ICP ppm	Al2O3 XRF %	CaO XRF %	Cr2O3 XRF %	Fe2O3 XRF %	K2O XRF %	MgO XRF %	MnO XRF %	Na2O XRF %	P2O5 XRF %	SiO2 XRF %	SO3 XRF %	TiO2 XRF %	LOI XRF %	SG pycnometer
I	9.15	5.70	0.80	0.49	36.16		2.91	0.11	14.53	0.85	0.06	0.05	3.85		0.02	33.65	2.98
I	9.14	6.00	1.10	0.50	36.16		2.90	0.11	14.56	0.85	0.06	0.05	3.90		0.02	33.75	2.96
I	9.17	6.00	1.00	0.49	36.37		2.91	0.11	14.64	0.85	0.06	0.05	3.87		0.02	33.65	2.94
I	9.22	5.80	1.00	0.49	36.11		2.88	0.11	14.53	0.85	0.05	0.05	3.89		0.02	33.66	2.94
I	9.23	5.70	1.00	0.49	36.14		2.88	0.11	14.50	0.85	0.05	0.05	3.91		0.02	33.66	2.97
I	9.24	6.00	1.10	0.51	36.11		2.88	0.11	14.58	0.84	0.05	0.05	3.88		0.02	33.54	2.98
I	9.14	6.00	1.00	0.50	36.08		2.88	0.11	14.56	0.85	0.04	0.05	3.88		0.02	33.58	2.95
I	9.11	6.20	1.10	0.50	36.18		2.89	0.11	14.56	0.85	0.05	0.05	3.87		0.02	33.58	2.95
J		6.50	1.20														2.83
J		6.70	1.10														2.85
J		6.90	1.30														2.88
J		6.70	1.00														2.89
J		6.60	1.00														2.88
J		6.70	1.50														2.85
J		7.30	1.10														2.87
J		6.80	1.20														2.86
L	9.34	6.96	1.23														2.89
L	8.95	6.89	1.23														2.89
L	9.02	6.87	1.22														2.89
L	9.89	6.68	1.18														3.01
L	9.25	6.64	1.16														2.94
L	9.47	6.67	1.16														2.99
L	9.74	6.18	1.18														2.89
L	9.11	7.13	1.22														2.93
M	9.03	6.90	1.90	0.48	36.68	0.01	3.15	0.01	15.76	0.92	0.04	0.04	3.85		0.02	33.84	2.93
M	8.93	7.60	1.20	0.44	36.41	0.01	3.18	0.02	15.80	0.92	0.07	0.04	3.87		0.02	33.84	2.96
M	8.58	6.80	1.10	0.47	36.50	0.01	3.17		15.85	0.92	0.04	0.04	3.87		0.03	33.81	3.01
M	8.79	6.20	1.20	0.49	36.44	0.01	3.16	0.02	15.66	0.92	0.06	0.04	3.84		0.02	33.75	3.02
M	9.07	6.50	0.90	0.41	36.74	0.01	3.14	0.02	15.74	0.91	0.07	0.04	3.90		0.02	33.81	2.95
M	9.09	7.30	1.10	0.41	36.56	0.01	3.18	0.01	15.71	0.91	0.04	0.04	3.81		0.02	33.77	3.01
M	8.87	7.40	1.00	0.48	36.38	0.01	3.13	0.01	15.86	0.91	0.05	0.04	3.81		0.02	33.77	2.96
M	8.84	6.40	1.00	0.47	36.37	0.01	3.16	0.01	15.66	0.91	0.04	0.03	3.89		0.03	33.80	2.94
O	8.77	6.50	1.30	0.41	36.30	0.01	2.95	0.11	14.50	0.85		0.03	3.91	1.70	0.01	33.25	2.84
O	8.79	6.70	1.30	0.40	36.30	0.01	2.93	0.11	14.50	0.85		0.03	3.89	1.72	0.01	33.48	2.86
O	8.83	6.30	1.20	0.40	36.10	0.01	2.92	0.11	14.55	0.85		0.03	3.86	1.68	0.01	33.39	2.88
O	8.90	6.30	1.20	0.41	36.30	0.01	2.92	0.10	14.50	0.85		0.03	3.86	1.71	0.02	33.31	2.87
O	8.75	6.60	1.20	0.40	36.30	0.01	2.95	0.11	14.55	0.88		0.03	3.90	1.71	0.01	33.80	2.88
O	8.76	6.70	1.30	0.40	36.20	0.01	2.95	0.11	14.50	0.85		0.03	3.86	1.74	0.01	33.53	2.87
O	8.70	6.30	1.20	0.40	36.40	0.01	2.95	0.11	14.55	0.85		0.03	3.93	1.75	0.01	33.73	2.88
O	8.61	6.40	1.20	0.40	36.30	0.01	2.93	0.11	14.60	0.86		0.03	3.93	1.74	0.01	33.58	2.88
P	9.11	6.40	1.20	0.51	36.10		2.99	0.18	14.50	0.86			4.04	1.60	0.03	33.73	2.95
P	9.17	6.40	1.10	0.51	36.20		2.95	0.18	14.50	0.85			4.06	1.58	0.03	33.77	2.95
P	9.22	6.30	1.20	0.51	36.10		2.94	0.18	14.40	0.85			3.94	1.52	0.02	33.76	2.96
P	9.08	6.10	1.10	0.54	36.10		2.95	0.18	14.50	0.85			4.13	1.52	0.03	33.68	2.94
P	9.07	6.60	1.20	0.49	36.20		3.00	0.18	14.40	0.84			3.96	1.55	0.03	33.66	2.95
P	8.52	6.20	1.00	0.49	36.10		2.96	0.18	14.40	0.84			3.91	1.44	0.03	33.78	2.98
P	8.95	6.70	1.20	0.50	36.40		2.97	0.18	14.60	0.85			4.06	1.56	0.03	33.65	2.95
P	8.47	6.40	1.10	0.48	36.20		2.95	0.18	14.50	0.85			3.92	1.57	0.02	33.71	2.95

12. Measurement of Uncertainty: The samples used in the certification process were selected in such a way as to represent the entire batch of material and were taken from the final packaged units; therefore all possible sources of uncertainty (sample uncertainty and measurement uncertainty) are included in the final combined standard uncertainty determination.

The uncertainty measurement takes into consideration the between lab and the within lab variances and is calculated from the square roots of the variances of these components using the formula:

$$\text{Combined standard uncertainty} = \sqrt{(\text{between lab. var./no of labs}) + (\text{mean square within lab. var./no of assays})}$$

These uncertainty measurements may be used, by laboratories, as a component for calculating the total uncertainty for method validation according to the relevant ISO guidelines.

Analyte	Method	Unit	S ¹	σ _L ²	Sw ³	CSU ⁴
F	ISE	%	0.232	0.159	0.162	0.057
U	M/ICP	ppm	0.391	0.270	0.258	0.090
Th	M/ICP	ppm	0.110	0.077	0.064	0.024
Al2O3	XRF	%	0.049	0.052	0.016	0.020
CaO	XRF	%	0.209	0.162	0.139	0.060
Fe2O3	XRF	%	0.032	0.025	0.025	0.011
K2O	XRF	%	0.026	0.030	0.003	0.011
MgO	XRF	%	0.449	0.459	0.071	0.163
MnO	XRF	%	0.034	0.038	0.007	0.014
P2O5	XRF	%	0.008	0.009	0.003	0.004
SiO2	XRF	%	0.100	0.082	0.054	0.028
TiO2	XRF	%	0.006	0.006	0.004	0.003
LOI	XRF	%	0.301	0.284	0.118	0.102
SG	pycnometer		0.043	0.036	0.025	0.013

1. S - Std Dev for use on control charts.
2. σ_L - Betw Lab Std Dev, for use to calculate a measure of accuracy.
3. Sw - Within Lab Stc Dev, for use to calculate a measure of precision.
4. CSU - Combined Standard Uncertainty, a component for use to calculate the total uncertainty in method validation.

13. Certified values: The Certified, Provisional and Indicated values listed on p1 of each certificate fulfill the AMIS statistical criteria regarding agreement for certification and have been independently validated by Dr Barry Smee, BSc, PhD, P.Geo, (B.C.).

14. Metrological Traceability: The values quoted herein are based on the consensus values derived from statistical analysis of the data from an inter laboratory measurement program. Traceability to SI units is via the standards used by the individual laboratories, the majority of which are accredited, who have maintained measurement traceability during the analytical process.

15. Certification: AMIS0250 is a new material.

16. Period of validity: The certified values are valid for this product, while still sealed in its original packaging, until notification to the contrary. The stability of the material will be subject to continuous testing for the duration of the inventory. Should product stability become an issue, all customers will be notified and notification to that effect will be placed on the www.amis.co.za website.

17. Minimum sample size: The majority of laboratories reporting used a 0.5g sample size for the ICP. This is the recommended minimum sample size for the use of this material.

18. Availability: This product is available in Laboratory Packs containing 1kg of material and Explorer Packs containing custom weights (from 50g to 250g) of material. The Laboratory Packs are sealed bottles delivered in sealed foil pouches. The Explorer Packs contain material in standard geochem envelopes, vacuum sealed in foil pouches.

19. Recommended use: The data used to characterize this CRM has been scrutinized using outlier treatment techniques. This, together with the number of participating laboratories, should overcome any "inter-laboratory issues" and should lead to a very accurate measure for the given methods, notwithstanding the underlying assumption that what the good inter-laboratory labs reported was accurate. However an amount of bad data might have had an effect, resulting in limits which in some situations might be too broad for the effective monitoring of a single analytical method, laboratory or production process. Users should set their own limits based on their own data quality objectives and control measurements, after determining the performance characteristics of their own particular method, using a minimum of 20 analyses using this CRM. User set limits should normally be within the limits recommended on p1 and 2 of this certificate.

20. Legal Notice: This certificate and the reference material described in it have been prepared with due care and attention. However AMIS, Set Point Technology (Pty) Ltd, Mike McWha, Dr Barry Smee and Smee and Associates Ltd; accept no liability for any decisions or actions taken following the use of the reference material.

26 June 2012

Certifying Officers:



African Mineral Standards: _____

Mike McWha
BSc (Hons), FGSSA, MAusIMM, Pr.Sci.Nat



Geochemist: _____

Barry W. Smee
BSc, PhD, P.Geo, (B.C.)

Appendix – uncertified trace element statistics

Analyte	Method	Unit	Mean	2SD	RSD%	n
Al	M/ICP	%	0.24	0.03	6.98	87
As	M/ICP	ppm	23.63	7.27	15.38	86
Ba	M/ICP	ppm	56.22	15.67	13.94	95
Be	M/ICP	ppm	0.17	0.08	24.03	85
Bi	M/ICP	ppm	0.09	0.04	22.98	70
Ca	M/ICP	%	24.26	2.16	4.46	76
Cd	M/ICP	ppm	4.79	0.66	6.89	89
Ce	M/ICP	ppm	23.31	4.00	8.57	89
Co	M/ICP	ppm	4.31	0.76	8.75	90
Cr	M/ICP	ppm	51.36	25.92	25.24	80
Cs	M/ICP	ppm	0.69	0.10	7.25	70
Cu	M/ICP	ppm	41.11	12.31	14.97	77
Dy	M/ICP	ppm	0.54	0.08	6.91	38
Er	M/ICP	ppm	0.35	0.07	10.54	40
Eu	M/ICP	ppm	0.19	0.03	7.25	39
Fe	M/ICP	%	2.04	0.16	3.87	90
Ga	M/ICP	ppm	0.91	0.52	28.54	91
Gd	M/ICP	ppm	0.66	0.10	7.74	39
Ge	M/ICP	ppm	0.10	0.13	60.67	31
Hf	M/ICP	ppm	0.19	0.08	21.56	85
Ho	M/ICP	ppm	0.11	0.02	8.93	39
In	M/ICP	ppm	0.02	0.01	21.12	68
K	M/ICP	%	0.10	0.02	7.95	91
La	M/ICP	ppm	16.51	2.83	8.57	89
Li	M/ICP	ppm	7.93	1.92	12.12	81
Lu	M/ICP	ppm	0.04	0.02	17.58	55
Mg	M/ICP	%	8.64	0.83	4.78	87
Mn	M/ICP	ppm	6298	493	3.92	91
Mo	M/ICP	ppm	0.79	0.31	19.44	88
Na	M/ICP	%	0.04	0.01	15.02	80
Nb	M/ICP	ppm	0.47	0.18	19.33	84
Nd	M/ICP	ppm	6.24	0.59	4.75	39
Ni	M/ICP	ppm	14.68	6.97	23.73	86
P	M/ICP	ppm	158.10	50.85	16.08	79
Pb	M/ICP	ppm	11.36	3.84	16.90	86
Pd	M/ICP	ppm	4.40	0.24	2.72	8
Pr	M/ICP	ppm	2.11	0.27	6.35	39
Rb	M/ICP	ppm	4.03	0.62	7.74	80
Re	M/ICP	ppm	0.00	0.00	27.26	32
S	M/ICP	%	0.70	0.11	7.51	87
Sb	M/ICP	ppm	1.46	0.41	14.06	87
Sc	M/ICP	ppm	0.57	0.59	51.81	49
Se	M/ICP	ppm	0.66	0.79	60.07	39
Si	M/ICP	%	1.95	0.04	1.06	8
Sm	M/ICP	ppm	0.69	0.04	3.05	35
Sn	M/ICP	ppm	0.41	0.43	52.87	50
Sr	M/ICP	ppm	41.24	5.80	7.03	94
Ta	M/ICP	ppm	0.34	0.66	97.54	25
Tb	M/ICP	ppm	0.09	0.04	22.83	64